



Chemical Village CO., LTD.

20/2 (B4), Teparak Rd, Bangplee Yai, Bangplee,
Samutprakarn, Thailand 10540

Tel : 66 2757 5290 **Fax :** 66 2757 5292

email : chemicalvillage@hotmail.com **website :** www.chemicalvillage.com

CARBON BLACK N326L

	Grades	N326L
Specification	Iodine Absorption Value g/Kg	88±5
	Oil Absorption Value (DBP) 10 ⁻⁵ m ³ /Kg	65±5
	CDBP Absorption Value of Compressed Sample 10 ⁻⁵ m ³ /Kg	83-93
	CTAB Absorption Surface Area CDBP Absorption Value of Compressed Sample 10 ⁻⁵ m ² /Kg	76-88
	STSA CDBP Absorption Value of Compressed Sample 10 ⁻⁵ m ² /Kg	75±5
	Nitrogen Surface Area 10 ⁻⁵ m ² /Kg	73-83
	Tinting Strength %	110±3
	Heating Loss %	2.5
	Fines Content %	10
	Sieve Residue (325 Mesh) ppm	1000
	Ash %	0.7
	Pour Density Kg/m ³	455±40
	Modulus at 300% Mpa.	-0.9±1 . 0
Application	Tread	O
	Carcass	O
	Inner Tube	
	Sidewall	
	Conveyor Belt	O
	Rubber Tube	O
	Rubber Roller	O
	Rubber Shoe	O
	Wire & Cable	O
	Industrial Rubber Product	O
Printing Ink	O	

NOTES:

O = Highly Recommended